PRIMAPAGE NEW white

Specification sheet





Primapage is a thin opaque uncoated paper dedicated to monochrome printing in either heat set or cold set. The combination of its natural brightness, excellent opacity, the low level of strike through plus a silky touch provides a finished publication which is "easy on the eyes". Primapage is available in both reels and sheets.

FSC® or PEFC certified on request

Specifications									
Characteristics	Unit	Standard							
Code			PPG29NEW	PPG33NEW	PPG36NEW	PPG40NEW	PPG45NEW	PPG50NEW	PPG60NEW
Grammage	g/m²	ISO 536	29 g/m ²	33 g/m ²	36 g/m ²	40 g/m ²	45 g/m ²	50 g/m ²	60 g/m ²
Basis weight (USA)	lbs	25*45/500	19,6	22,3	24,3	27,0	30,4	33,8	40,5
Thickness	μm	ISO 534	33,9	38,6	42	47	52,7	58,5	70,2
Bulk	cm³/g	-	1,17	1,17	1,17	1,17	1,17	1,17	1,17
PPI (indicative)	pages/inch	T 411	1 554	1 320	1 226	1 090	966	880	720
Whiteness	%	ISO 2470	86	87,5	87,5	87,5	87,5	87,5	87,5
Opacity	%	ISO 2471	80	79,5	80	82	84	86	88
Absolute humidity	%	NF Q03-003				5,7			
Permanent paper	-	ISO 9706	OUI						
Optical brightner	-	-	NON						

Paper tolerances					
Grammage: nominal value + / - 1 g/m²	ISO whiteness minimum: nominal value 1 point				
Thickness: + / - 2 μm	ISO opacity minimum: nominal value 1 point				
PPI (indicative)	Absolute humidity: + / - 0.5%				

Finished goods tolerances					
Joins: maximum of 2 joins per reel with at least 60% of the reels being "join free"					
Width: customer width - 0 mm, + 2 mm					
Outer diameters of 100 cm, 114 cm or 120 cm: - 3 cm, + 2 cm					

Minimum making: Quantity required by the mill will be dependent on both the production schedules and the possibilities at the time of the order for a combination of widths to cover the machine deckle.

Please contact your sales representative for more details.

Measurements made on Jumbo rolls according to the Standards and Norms in place at that time.

Validated: February 2017

Qualified by Hervé Brunet-Jailly - Product Manager